



Declarations of Performance

DOP MHP 18_552

According to the regulation (EU) No. 305/2011

- Identification code of the product type:
3-layer solid wood panel DIN EN 13353:2022 for use in construction as load-bearing components outdoors, SWP/3 S, L3, 16-60 mm
- Type, batch or serial number or another identifier for identifying the construction product according to article 11 paragraph 4 BauPVo:
The manufacturer can find out the production date from the barcode on the packaging label. The panel thickness, top layer thickness, wood type, quality and format of the panel are also shown on the label.
- Intended use of the construction product according to the harmonized technical specification:
Use according to DIN EN 13353:2022, SWP/3 S: Solid wood panels for load-bearing outdoor use
- Name, registered trade name or brand and address of the manufacturer according to article 11 paragraph 4 BauPVo:
**Pfeifer Holz s.r.o.
Chanovice 102
CZ – 341 01 Horazdovice
Tschechische Republik**
- System for assessment and verification of constancy of performance according to Annex V of BauPVo:
System 2+
- If the construction product is regulated by a harmonized standard:
The development and testing laboratory Holztechnologie GmbH (NB No.0766) carried out the initial inspection of the factory and the factory production control as well as the ongoing monitoring, assessment and evaluation of the factory production control according to the system 2+ and issued a certificate of conformity. Valid Certificate - Number 0766 - CPR - 552.
- Declared Performance:

Technical values of multi-layer solid wood panels DIN EN 13353:2022

1,2	nominal thickness mm	strength	Characteristic density (kg/m ³) and strength (N/mm ²) DIN EN 12369-3:2022											
			Bending perpendicular to plate plane		Bending at plate level		tensile at plate level		compressive at plate level		shear perpendicular to plate plane		shear at plate level	
			$f_{m,flat}$		$f_{m,edge}$		f_t		f_c		$f_{v,edge}$		$f_{v,flat}$	
	t_{nom}	ρ	0	90	0	90	0	90	0	90	0	90	0	90
	12 bis 20	410	30	5	25	12	12	3	18	12	4	4	1,0	1,0
	>20 bis 30	410	27	5	18	12	9	3	16	10	4	4	1,0	1,0
	>30 bis 80	410	20	10	12	12	6	3	10	10	2,5	2,5	1,0	1,0
3	Quality of the bonding		SWP/3 according to DIN EN 13354:2008; pretreatment 3; $0,8 \leq f_v \leq 1,2$ n/mm ² (in the case of broken timber ≥ 20 %)											
4	Transverse tensile strength		NPD											
5	Durability (thickness swelling)		NPD											
6	Formaldehyde release		E1 (DIN EN 717-1, the test result was multiplied by a factor of 2)											
7	Reaction to fire		reaction to fire class		minimum thickness				end use condition					
			D-s2, d0		12 mm				without an air gap behind the material					
					15 mm				with a closed air gap behind the material					
					18 mm				with an open air gap behind the material					
D-s2, d2		12 mm				with closed or open air gap of not more than 22 mm behind the timber material								

8	Water vapour permeability	medium density 300kg/m ³ : μ moist 50, μ dry 150 medium density 500kg/m ³ : μ moist 70, μ dry 200											
9	Airborne sound insulation	R= 13 x lg (mA) + 14											
10	Sound absorption	Frequency range 250 Hz – 500 Hz: 0,10 Frequency range 1 000 Hz – 2 000 Hz: 0,30											
11	Thermal conductivity	medium density 300kg/m ³ : λ 0,09 W/mK medium density 500kg/m ³ : λ 0,13 W/mK											
12	nominal thickness mm	Mittlere Steifigkeitswerte (N/mm²) DIN EN 12369-3:2022											
		Bending perpendicular to plate plane		Bending at plate level		tensile at plate level		compressive at plate level		shear perpendicular to plate plane		shear at plate level	
	<i>t_{nom}</i>	<i>E_{m,flat}</i>		<i>E_{m,edge}</i>		<i>E_t</i>		<i>E_c</i>		<i>G_{edge}</i>		<i>G_{flat}</i>	
		0	90	0	90	0	90	0	90	0	90	0	90
		12 bis 20	10 000	650	6 000	4 000	6 000	4 000	6 000	4 000	450	450	50
>20 bis 30	10 000	800	5 000	4 000	5 000	4 000	3 500	2 500	450	450	50	50	
>30 bis 80	8 000	1 500	4 000	4 000	4 000	4 000	2 500	2 500	450	450	50	50	
13	Mechanical durability	NPD											
14	Biological durability	NPD											
15	Content of pentachlorophenol	≤ 5 ppm											
16	Shear wall load capacity	NPD											
17	Bearing strength	NPD											

8. The performance of the product according to numbers 1 and 2 corresponds to the declared performance according to number 7. The manufacturer is solely responsible for the creation of this declaration of performance according to number 4.

Signed on behalf of the manufacturer:

Chanovice, 29.04.2024:



Vlastimil Kuba / Managing Director

Signature / Stamp